



**SHERWIN  
WILLIAMS.**

**PROCLASSIC®**

**INTERIOR ALKYD SATIN  
B33W220 SERIES**

| <u>CHARACTERISTICS</u>   | <u>SPECIFICATIONS</u> | <u>SURFACE PREPARATION</u> |          |             |     |      |   |   |
|--|-----------------------|----------------------------|----------|-------------|-----|------|---|---|
| <p><b>ProClassic® Interior Alkyd Satin Enamel</b> is our finest quality alkyd satin product. The superior flow and leveling characteristics result in a smooth and durable finish.</p> <p><b>Project Uses</b></p> <ul style="list-style-type: none"> <li>• all trim areas and moulding</li> <li>• cabinets/doors/windows</li> <li>• kitchen's/baths/locker rooms</li> <li>• laundry rooms</li> <li>• high traffic areas</li> </ul> <p><b>Substrates</b></p> <ul style="list-style-type: none"> <li>• drywall/plaster</li> <li>• paneling/wood</li> <li>• metal</li> <li>• concrete/masonry</li> <li>• wallcovering</li> </ul> <p><b>Color:</b> Many Colors</p> <p><b>Coverage:</b> 350-400 sq ft/gal<br/>@ 4 mils wet; 1.8 mils dry</p> <p><b>Drying Time, @ 77°F, 50% RH:</b><br/>temperature and humidity dependent</p> <p>Touch: 4-6 hours<br/>Recoat: 24 hours</p> <p><b>Finish:</b> 25-35 units @ 60°</p> <p><b>Flash Point:</b> 110°F, PMCC</p> <p><b>Tinting with Blend-A-Color:</b></p> <table border="1"> <thead> <tr> <th>Base</th> <th>oz/gal</th> <th>Strength</th> </tr> </thead> <tbody> <tr> <td>Extra White</td> <td>0-5</td> <td>100%</td> </tr> </tbody> </table> <p><b>Vehicle Type:</b> Alkyd</p> <p><b>B33W221</b></p> <p><b>VOC (less exempt solvents):</b><br/>446 g/L; 3.72 lb/gal</p> <p><b>Volume Solids:</b> 43 ± 2%</p> <p><b>Weight Solids:</b> 63 ± 2%</p> <p><b>Weight per Gallon:</b> 10.0 lb</p> <p>Not OTC Compliant</p> | Base                  | oz/gal                     | Strength | Extra White | 0-5 | 100% | <p><b>Block</b></p> <p>1 ct. Loxon Block Surfacers<br/>2 cts. ProClassic Interior Alkyd Satin</p> <p><b>Drywall</b></p> <p>1 ct. PrepRite Classic Primer<br/>2 cts. ProClassic Interior Alkyd Satin</p> <p><b>Plaster</b></p> <p>1 ct. PrepRite Classic Primer<br/>2 cts. ProClassic Interior Alkyd Satin</p> <p><b>Masonry</b></p> <p>1 ct. PrepRite Masonry Primer<br/>2 cts. ProClassic Interior Alkyd Satin</p> <p><b>Wood, Composition Board</b></p> <p>1 ct. PrepRite Wall and Wood Primer<br/>2 cts. ProClassic Interior Alkyd Satin</p> | <p><b>WARNING!</b> Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p>Remove all surface contamination by washing with ProClean Professional® Prep Wash Concentrated Cleaner or other appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with PrepRite® ProBlock® Primer Sealer.</p> <p><b>Drywall</b></p> <p>Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.</p> <p><b>Masonry, Concrete, Cement, Block</b></p> <p>All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite® Masonry Primer.</p> |
| Base   | oz/gal                | Strength                   |          |             |     |      |   |   |
| Extra White  | 0-5                   | 100%                       |          |             |     |      |   |   |

103.24

# PROCLASSIC®

## INTERIOR ALKYD SATIN

### B33W220 SERIES



**SHERWIN  
WILLIAMS®**

| <u><b>SURFACE PREPARATION</b></u>  | <u><b>APPLICATION</b></u>   | <u><b>CAUTIONS</b></u>   |
|--|---|--|
| <p><b>Plaster</b><br/>Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.</p> <p><b>Wood</b><br/>Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.</p> <p><b>Mildew</b><br/>Remove before painting by washing with ProClean Professional Mildew Eliminator or a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.</p> <p><b>Caulking</b><br/>Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate Pro Select® caulk after priming the surface.</p> | <p>Apply at temperatures above 50°F. No reduction necessary.</p> <p><b>Brush</b><br/>Use a natural bristle brush.</p> <p><b>Roller</b><br/>Use a 1/4" - 3/4" nap synthetic or lambs-wool roller cover.</p> <p><b>Spray-Airless</b><br/>Pressure ..... 2000 psi<br/>Tip ..... .015"-.017"</p> <p><u><b>CLEANUP INFORMATION</b></u></p> <p>Clean spills, spatters, hands and tools immediately after use with mineral spirits. Follow manufacturer's safety recommendations when using mineral spirits.</p> | <p>Non-photochemically reactive.</p> <p>LABEL CAUTION<br/>CAUTION contains ALIPHATIC HYDROCARBONS. Contents are COMBUSTIBLE. Keep away from heat and open flame. VAPOR HARMFUL. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water for 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water. In case of respiratory difficulty, provide fresh air and call physician. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Contains solvents which can cause permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.<br/>HOTW 11/17/2004 B33W00221 09 00</p> <p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.</p> |