

102.14



Duration™

EXTERIOR LATEX SATIN COATING

K33 SERIES

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Most coating failures are due to inadequate surface preparation or application. Thorough surface preparation will help provide long term protection with DURATION coating. Remove all surface contamination, including mildew and chalk, by washing with ProClean Professional™ Prep Wash Concentrated Cleaner or other cleaner, rinse thoroughly and allow to dry. Scrape and sand existing peeled or cracked paint to a sound surface. Remove any oil or grease with a water-based degreasing cleaner. Sand glossy surfaces dull. All rust must be removed. Seal stains from water, smoke, graffiti, grease, etc. with PrepRite ProBlock Primer/Sealer.

Caulking—After cleaning the surface thoroughly, caulk around windows, doors, and other openings with Pro Select™ Premium Siliconized Acrylic Latex Caulk 1100A after spot priming any bare surfaces in these areas with DURATION or other appropriate primer.

Aluminum and Galvanized Steel - Wash with ProClean Professional™ Prep Wash Concentrated Cleaner or other water based degreasing cleaner to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, steel wool, or other abrading method. After cleaning any corrosion from galvanized steel, apply 1 coat of **All Surface Enamel Primer**.

Cement Composition Siding/Panels - Pressure clean, if needed, with a minimum of 2100 psi pressure to remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, and peeling or defective coatings. Allow the surface to dry thoroughly. If the surface is new, test it for pH, if the pH is higher than 8, prime with **Loxon Masonry Primer**.

SURFACE PREPARATION

Cement, Concrete, Masonry, Block - All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with **Loxon Masonry Primer**. If a smoother finish is desired on rough surfaces, use **Loxon Block Surfacer or PrepRite Block Filler**.

After power washing, previously painted masonry may still have a powdery surface that should be sealed with **Loxon Conditioner** and then apply 1 coat of **DURATION**.

Composition Board/Hardboard — Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. Because of the potential for wax bleeding out of the substrate, we recommend 1 coat of **A-100® Exterior Oil Primer** and then 1 coat of **DURATION**.

Exterior Drywall - Fill cracks and holes with an exterior grade patching paste/spackle and sand smooth. Remove all sanding dust.

Steel - Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. To prevent surface rusting on bare steel, apply 1 coat of **All Surface Enamel Primer** and then 1 coat of **DURATION**.

Stucco - Remove any loose stucco, efflorescence, or laitance. Allow new stucco to cure at least 30 days before painting. If painting cannot wait 30 days, allow the surface to dry 5-7 days and prime with **Loxon Acrylic Primer**.

Vinyl Siding - Clean the surface thoroughly by scrubbing with warm, soapy water. Rinse thoroughly. Do not paint vinyl siding with any color darker than the original color. Painting with darker colors may cause the siding to warp.

Wood - Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. Knots and some woods, such as redwood and cedar, contain a high amount of tannin, a colored wood extract. If applied to these bare woods, the first coat of **DURATION** may show some staining, but it will be trapped in the first coat. A second coat will uniform the appearance. If staining persists, spot prime severe areas with 1 coat of **A-100 Exterior Oil Wood Primer** prior to using **DURATION**.

CAUTIONS

For exterior use only.
Protect from freezing.
Non-photochemically reactive.

LABEL CAUTIONS

CAUTION contains ANTIMONY, CRYSTALLINE SILICA, and ZINC. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, Call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN. Do not apply on toys and other children's articles or furniture.
LCE 10/26/01 K33W15 02 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.